



Mirafi[®] MPV600

Mirafi[®] MPV600 is a heat-set, nonwoven, polypropylene geotextile with high asphalt absorption, specifically designed for asphalt overly applications. Mirafi[®] MPV600 meets the AASHTO M 288-00 specification for paving fabrics. Mirafi[®] MPV600 is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	kN (lbs)	0.54 (120)	0.54 (120)
Grab Tensile Elongation	ASTM D 4632	%	50	50
Mullen Burst Strength	ASTM D 3786	kPa (psi)	1585 (230)	
Asphalt Retention	ASTM D 6140	l/m ² (gal/yd ²) (oz/ft ²)	1.18 (0.26) (3.7)	
Melting Point	ASTM D 276	°C (°F)	163 (325)	
Mass per Unit Area	ASTM D 5261	g/m ² (oz/yd ²)	156 (4.6)	
UV Resistance after 500 hours	ASTM D 4355	% Strength Retained	70	

Physical Properties	Unit	Typical Value
Roll Width	m (ft)	3.81 (12.5)
Roll Length	m (ft)	110 (360)
Roll Area	m ² (yd ²)	418 (500)
Estimated Roll Weight	kg (lbs)	80 (178)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.